

N-048

NEOPRENE SEALANT

DESCRIPTION:

x'traseal® N-048 Neoprene is a one part sealer mainly consists neoprene rubber and synthetic resin. It is a special formulated sealant that cures to a tough, flexible bond to all engineering material surfaces. Because of its excellent elasticity and water resistivity, it is most suitable for water-proofing, dust-proofing and hermetically sealing of **containers**, cabins, bus, mobile homes and various appliances.

FEATURES:

- ◆ Outstanding durability.
- ◆ One parts no mixing.
- ◆ Good adhesion and excellent elasticity to metals, woods, plastics, glass and many other engineering materials.
- ◆ 100% weather proof.
- ◆ Permanently flexible under stress to normal expansion and compression.
- ◆ Quick curing at room temperature.
- ◆ Excellent gunnability.
- ◆ Very stable properties in composite container.

USES:

- ◆ For joints of containers.
- ◆ For joints of automobiles, bus and other vehicles.
- ◆ Sealing of joints in zinc roofs and slate roofs.

WE RECOMMEND PRELIMINARY COMPATIBILITY TESTS PRIOR TO APPLICATION TO ACHIEVE DESIRABLE RESULTS

NOT RECOMMENDED FOR:

N-048 Neoprene Sealant is not suitable for high joint movement substrate.

COLOUR:

Grey. Other colours are available upon request.

APPLICATION:

- ◆ Surface must be clean and dry.
- ◆ Cut nozzle to desired size.
- ◆ Insert cartridge into caulking gun.
- ◆ Push sealant ahead for uniform bead.
- ◆ Tool within 5 minutes.
- ◆ Clean off excess sealant with M.E.K. Or toluene.

SPECIFICATION:

Base	Neoprene Rubber
Appearance	Non-Sagging Paste
Solvent	Aromatic Solvent Blend
Specific Gravity	1.15 ± 0.05
Solid Contents	76 ± 5%
Shore A Hardness	35 Approx.
Tensile Strength	1.2 Mpa
Tack Free Time	10 Minutes Approx.
Application Temp.	-10°C To 50°C
Service Temp.	-50°C To 100°C
Shelf Life	12 Months

STORAGE:

Material should be stored in a dry and cool place between +5°C TO +30°C.

CAUTION:

Highly flammable. Read and understand material safety data sheet of this product before handling or using.

This information is provided in good faith and is believed accurate based on a review of current composition and information supplied by vendors. No warranty is expressed or implied. Liability is expressly disclaimed.

