

WOOD FILLER



ISO 9001

DESCRIPTION:

x'traseal® WOOD FILLER IS A CELLULOSE FIBRE READY MIXED HIGH PERFORMANCE WATER BASED FILLER THAT GIVE A TOUGH AND SMOOTH SANDABLE SURFACE AFTER DRIED, IT CAN BE STAINED, VARNISHED, PAINTED AND ACT LIKE REAL WOOD.

FEATURES:

- ◆ LOW ODOR.
- ◆ HARD AND SMOOTH SURFACE.
- ◆ ONE PART NO MIXING.
- ◆ ENVIRONMENTAL FRIENDLY, EASILY CLEAN UP WITH WATER BEFORE CURED.
- ◆ GOOD ADHESION TO WOOD, CONCRETE, METAL AND MARBLE.

USES:

- ◆ DIY APPLICATION: FURNITURE, PANELLING, DOORS, PLYWOOD PATCHING.

WE RECOMMEND PRELIMINARY COMPATIBILITY TESTS PRIOR TO APPLICATION TO ACHIEVE DESIRABLE RESULTS

NOT RECOMMENDED FOR:

NOT FOR: USE IN AREAS OF CONSTANT WATER IMMERSION.
NOT FOR: JOINT MOVEMENT.

COLOUR:

NATURAL, TEAK.

APPLICATION:

- ◆ SURFACE TO BE FILLED MUST BE CLEAN AND DRY.
- ◆ MASK SMOOTH SURFACE TO SIMPLIFY CLEAN UP.
- ◆ APPLY WOOD FILLER FIRMLY INTO PLACE WITH A PUTTY KNIFE.
- ◆ FILL UP SLIGHTLY HIGHER SURFACE TO ALLOW FOR SANDING.
- ◆ SAND AFTER 30MINUTES ON SHALLOW REPAIRS, DEEP REPAIRS AFTER 2-8HOURS.
- ◆ USE MEDIUM SAND PAPER, DO NOT CONTINUOUS HIGH SPEED SANDING.

CURING TIME:

WOOD FILLER WILL DRIED IN APPROXIMATELY 30 MINUTES AND WILL CURE TO A DEPTH OF 5mm IN 1-2DAYS. LONGER CURING TIME MAY BE NECESSARY IN COLD AND HIGH HUMIDITY AREA.

SPECIFICATION:

BASE	VINYL ACETATE LATEX
APPEARANCE	NON-SAGGING PASTE
COLOUR	NATURAL, TEAK.
SPECIFIC GRAVITY	1.65 ± 0.05
SOLID CONTENTS	80 ± 2%
TACK FREE TIME	10 MINUTES APPROX.
APPLICATION TEMP.	5°C TO 50°C
SERVICE TEMP.	-10°C TO 80°C
SHelf LIFE	12 MONTHS

STORAGE:

MATERIAL SHOULD BE STORED IN A DRY AND COOL PLACE BETWEEN +5°C TO +30°C.

CAUTION:

READ AND UNDERSTAND MATERIAL SAFETY DATA SHEET OF THIS PRODUCT BEFORE HANDLING OR USING.

This information is provided in good faith and is believed accurate based on a review of current composition and information supplied by vendors. No warranty is expressed or implied. Liability is expressly disclaimed.

