

# 750°F XTRA GRAY PLUS



ISO 9001

## RTV GASKET MAKER (NEUTRAL)

### DESCRIPTION:

**x'traseal® 750°F XTRA GRAY PLUS RTV GASKET MAKER** IS A ONE PART SILICONE SEALANT THAT CURE TO FORM A DURABLE RUBBER SEAL THAT OFFER EXCELLENT ADHESION, HEAT RESISTANT FOR GLAZING AND JOINT SEALING APPLICATION.

### FEATURES:

- ◆ LOW ODOR NEUTRAL CURING SYSTEM.
- ◆ NON-CORROSIVE TO METALS.
- ◆ NON-CORROSIVE TO AUTOMOBILES.
- ◆ OUTSTANDING HIGH TEMPERATURE RESISTANT UPTILL 371°C.
- ◆ EXCELLENT GUNNABILITY (-20°C TO 50°C).
- ◆ PRIMERLESS ADHESION TO MOST MATERIALS.

### USES:

- ◆ HIGH TEMPERATURE RESISTANT GASKET AND JOINT SEALING.
- ◆ ASSEMBLIES OF GLASS, PORCELAIN COATED METAL, EPOXY AND POLYESTER PANELS, POLYSTYRENE, ANODISED ALUMINIUM AND FINISHED WOOD.

**WE RECOMMEND PRELIMINARY COMPATIBILITY TESTS PRIOR TO APPLICATION TO ACHIEVE DESIRABLE RESULTS**

### NOT RECOMMENDED FOR:

NOT FOR: 750°F XTRA GRAY RTV SILICONE IS NOT PAINTABLE.  
 NOT FOR: PE, PP, PTFE AND BITUMINOUS SURFACE.  
 NOT FOR: PARTS IN CONTACT WITH GASOLINE.

### APPLICATION:

- ◆ REMOVE OLD GASKET MATERIAL FROM SURFACES THOROUGHLY.
- ◆ CLEAN SURFACE WITH RESIDUE-FREE SOLVENT AND ALLOW SURFACE TO DRY.
- ◆ CUT NOZZLE TO DESIRED SIZE.
- ◆ SQUEEZE TUBE TO FORM A CONTINUOUS AND EVEN BEAD TO THE PERIMETER OF MATING SURFACE AND ALL BOLT HOLES.
- ◆ TOOL WITHIN 5 MINUTES.
- ◆ TIGHTENED TO THE REQUIRED TORQUE, DO NOT OVERTIGHTEN.
- ◆ CLEAN OFF EXCESS SEALANT WITH M.E.K. OR TOLUENE.

### CURING TIME:

750°F XTRA GRAY RTV SILICONE WILL TACK FREE IN APPROXIMATELY 15 MINUTES AND WILL CURE TO A DEPTH OF 13mm WITHIN 7 DAYS. LONGER CURING TIME MAY BE NECESSARY IN DRY AND LOW HUMIDITY AREA.

### SPECIFICATION:

CURING SYSTEM	NEUTRAL (OXIME)
APPEARANCE	NON-SAGGING PASTE
ODOUR	OXIME SMELL
SPECIFIC GRAVITY	1.40 ± 0.05
SHORE A HARDNESS	38 APPROX.
ELONGATION	200% APPROX.
TENSILE STRENGTH	2.0 MPa APPROX.
TACK FREE TIME	15 MINUTES
APPLICATION TEMP.	-20°C TO 50°C
SERVICE TEMPERATURE	-40°C TO 371°C.
SHELF LIFE	12 MONTHS

### STORAGE:

MATERIAL SHOULD BE STORED IN A DRY AND COOL PLACE BETWEEN +5°C TO +30°C.



# 750°F XTRA GRAY PLUS

## RTV GASKET MAKER (NEUTRAL)



ISO 9001

**CAUTION:**

READ AND UNDERSTAND MATERIAL SAFETY DATA SHEET OF THIS PRODUCT BEFORE HANDLING OR USING.

*This information is provided in good faith and is believed accurate based on a review of current composition and information supplied by vendors. No warranty is expressed or implied. Liability is expressly disclaimed.*

