

CA-288

CONTACT ADHESIVE



ISO 9001

DESCRIPTION:

x'traseal® CA-288 CONTACT ADHESIVE WHICH HAVE MEDIUM VISCOSITY, LONG TACK TIME, EASY TO APPLY, COST SAVING AND STRONG BONDING STRENGTH.

USES:

- ◆ CA-288 IS MOST SUITABLE FOR GENERAL PURPOSE, LIGHT INDUSTRY, FURNITURE, CONSTRUCTION AND DECORATION INDUSTRY.
- ◆ BONDING OF RUBBER, WOOD, PLYWOOD, SPONGE, FORMIC, PVC CARPET, CEMENT, METAL, CLOTH AND PAPER PRODUCT.

METHOD OF USE:

- ◆ WIPE OFF MOISTURE, OIL AND ALL OTHER FOREIGN MATTERS ON BONDING SURFACES.
- ◆ APPLY A THIN LAYER OF CA-288 ON THE BONDING SURFACES EVENLY. FOR EFFECTIVE BONDING ON ABSORBENT SURFACES AND POROUS MATERIAL NORMALLY TWO COATS ARE REQUIRED.
- ◆ FOR BONDING SURFACES ASSEMBLE UNDER ROOM TEMPERATURE THE RECOMMENDED TIME IS 15 TO 30 MINS.
- ◆ FOR BONDING SURFACES WITH HIGHER ABSORBENT RATE THE OPEN TIME SHALL BE SHORTER BUT FOR SMOOTH BONDING SURFACES THE OPEN TIME SHALL BE LONGER.
- ◆ AFTER ASSEMBLE APPLY SUITABLE PRESSURE ON THE BONDING SUBSTRATES.
- ◆ BOND STRENGTH CAN BE FULLY OBTAINED AFTER 24 HOURS.
- ◆ APPLICATION SHOULD BE CARRIED OUT IN A WELL VENTILATED AREA.

SPECIFICATION:

APPEARANCE	BROWN YELLOWISH
PRINCIPAL COMPOSITION	CHLOROPRENE RUBBER
VISCOSITY	3,000 – 4000 CPS
SOLID CONTENT	17 – 22%
SPECIFIC GRAVITY	0.89 - 0.92
FLASH POINT	HIGHLY FLAMMABLE
SHELF LIFE	12 MONTHS

STORAGE:

MATERIAL SHOULD BE KEPT IN A WELL-SEALED CONTAINER AND STORED IN A DRY AND COOL PLACE BETWEEN +5°C TO +30°C.

CAUTION:

READ AND UNDERSTAND MATERIAL SAFETY DATA SHEET OF THIS PRODUCT BEFORE HANDLING OR USING.

This information is provided in good faith and is believed accurate based on a review of current composition and information supplied by vendors. No warranty is expressed or implied. Liability is expressly disclaimed.

