

BT-330

Instant Flashing Tape



ISO 9001

DESCRIPTION:

x'traseal® BT-330 INSTANT FLASHING TAPE IS A BLACK, VERSATILE, SELF-ADHESIVE TAPE, COMPRISING AN ELSTOPLASTIC WEATHERPROOF BITUMEN COMPOUND COVERED BY A REINFORCES ALUMINIUM FILM. BITUMINOUS COMPOUND IS PROTECTED BY A SILICONIZED RELEASE FILM.

TOTAL THICKNESS 1.50MM (0.059IN)

WIDTH & LENGTH OF ROLL:

ROLL WIDTH	ROLL LENGTH
50MM	10 METERS (11 YARDS)
75MM	10 METERS (11 YARDS)
100MM	10 METERS (11 YARDS)

FEATURES:

- ♦ EASY TO APPLY
- ♦ WEATHERPROOF
- ♦ OUTSTANDING DURABILITY
- ♦ COST SAVING

USES:

- ♦ PROTECTION:
ASPHALT, BRICKWORK, CONCRETE, FIBER CEMENT SHEETS, METAL AND PLASTIC MATERIALS ON ROOFS AND COVERING IN GENERAL.
- ♦ SEALING & WATERPROOFING:
GLASS & PLASTIC WINDOW FRAMES, PARAPETS, SKYLIGHTS STRUCTURES, ETC.
- ♦ REPAIR WORK:
METAL AND FIBER CEMENT SHEETS ROOFING, SHINGLES, GUTTERS AND METAL TUBE.

WE RECOMMEND PRELIMINARY COMPATIBILITY TESTS PRIOR TO APPLICATION TO ACHIEVE DESIRABLE RESULTS

APPLICATION:

- ♦ SURFACES MUST BE CLEAN, DUST-FREE AND DRY. RUST SHOULD BE REMOVED.
- ♦ CRACKS WIDER THAN 3MM SHOULD BE FILLED.
- ♦ REMOVE INSTANT FLASHING TAPE FROM THE RELEASE PAPER AND PRESS IT INTO POSITION USING FINGERTIP PRESSURE.
- ♦ USE A SEAM ROLLER TO SMOOTH OVER INSTANT FLASHING TAPE TO ENSURE GOOD CONTACT IS MADE.

PHYSICAL PROPERTIES:

SURFACE	PE COATED ALUMINIUM
ADHESIVE	BITUMINOUS COMPOUND
LINER	SILICONIZED FILM
THICKNESS	1.33M (0.052IN)

SPECIFICATION:

TENSILE STRENGTH	65 N/MM ²
TEAR STRENGTH	18 N/MM ²
ELONGATION	11 % APPROX.
SOFTENING POINT	+ 95°C
COLD FLEXIBILITY	> -40°C
ADHESION ON STEEL	5.8 N/MM ²
UV RESISTANCE	GOOD
SERVICE TEMPERATURE	-40°C TO 80°C
SHELF LIFE	12 MONTHS

STORAGE:

MATERIAL SHOULD BE STORED IN A DRY AND COOL PLACE BETWEEN +5°C TO +30°C.

NOTE:

DO NOT APPLY INSTANT FLASHING TAPE IF SURFACE TEMPERATURE IS BELOW 5°C.
INSTANT FLASHING TAPE WILL BECOME BRITTLE IF ENCASED IN A CEMENTITIOUS MIX.
INSTANT FLASHING TAPE IS NOT RESISTANT TO ACID AND ALKALINE.

CAUTION:

READ AND UNDERSTAND MATERIAL SAFETY DATA SHEET OF THIS PRODUCT BEFORE HANDLING OR USING.

This information is provided in good faith and is believed accurate based on a review of current composition and information supplied by vendors. No warranty is expressed or implied. Liability is expressly disclaimed.

